



Georgian Bay Reinforcement Fabrics

999 William Street, P.O. Box 459
Midland, Ontario
L4R 4L3 Canada

Telephone: 705-527-5404
Fax: 705-527-0258

WOVEN TAPE PRODUCT SPECIFICATION

Issued June, 2002
Revised June, 2004

Product: **T0621-A00**

	<u>Metric</u>	<u>SAE</u>	
Style:	T0621	T0621	
Finish: (Silane Direct Size Yarn)	A00	A00	
Weave:	Plain	Plain	
Construction	Warp: 72.2 /10cm (+/- 4) Weft: 69.0 /10cm (+/- 4)	18.3 /inch (+/- 1) 17.5 /inch (+/- 1)	ASTM D-3775
Yarn	Warp: 134 tex Weft: 2 x 66 tex	G37 1/0 2 x G75 1/0	
Weight	190 g/m ² (+/-5%)	5.5 oz/yd ² (+/- 5%)	ASTM D-3776
Thickness:	0.203 mm (+/-0.05)	0.008 inches (0.002)	ASTM D-1777
Available Widths:	25 mm to 350 mm	1 inch to 14 inch	

All values above are nominal and are to be used as guidelines.

Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.

Georgian Bay Reinforcement Fabrics